



# AS4030SS-H

## Technical Data Sheet

## Air Filtration



### Meltblown Media

100% polypropylene meltblown media, typically designed for pocket and rigid filter applications.

		Target	Specification	Test Method
CLASSIFICATION(S):	EN779 - 2002	F5		
BASIS WEIGHT:	(g/m <sup>2</sup> )	100	86-114	EN/ISO 536
THICKNESS:	(mm)	-	-	EN/ISO 534 0.1 N/cm <sup>2</sup>
Air permeability	(l/m <sup>2</sup> s)	1815	1385-2245	EN/ISO 9237
AIRFLOW RESISTANCE:	(Pa)	12.5	9-16	TSI 8130, 11 cm/sec (21.6 FPM) face velocity
EFFICIENCY:	(% with 0.3 micron DEHS)	42	24-60	TSI 8130, 11 cm/sec (21.6 FPM) face velocity
FLAMMABILITY DATA:	DIN 53438	F1		
	UL			

All product data and statements are indicative of typical properties and characteristics obtainable. This data sheet is to be used as a guide and not as a specification sheet. H&V makes no representation or warranty except as otherwise agreed to in writing between the parties.