



AS6030SS-H

Technical Data Sheet

Air Filtration



Meltblown Media

100% polypropylene meltblown media, typically designed for pocket and rigid filter applications.

| | | Target | Specification | Test Method |
|---------------------|--------------------------|--------|---------------|---|
| CLASSIFICATION(S): | EN779 - 2002 | F6 | | |
| BASIS WEIGHT: | (g/m ²) | 104 | 90-118 | EN/ISO 536 |
| THICKNESS: | (mm) | - | - | EN/ISO 534 0.1 N/cm ² |
| Air permeability | (l/m ² s) | 1080 | 740-1420 | EN/ISO 9237 |
| AIRFLOW RESISTANCE: | (Pa) | 22 | 9-35 | TSI 8130, 11 cm/sec (21.6 FPM) face velocity) |
| EFFICIENCY: | (% with 0.3 micron DEHS) | 57 | 44-70 | TSI 8130, 11 cm/sec (21.6 FPM) face velocity) |
| FLAMMABILITY DATA: | DIN 53438 | F1 | | |
| | UL | | | |

All product data and statements are indicative of typical properties and characteristics obtainable. This data sheet is to be used as a guide and not as a specification sheet. H&V makes no representation or warranty except as otherwise agreed to in writing between the parties.