



# AS8030SS-H

## Technical Data Sheet

## Air Filtration



### Meltblown Media

100% polypropylene meltblown media, typically designed for pocket and rigid filter applications.

		Target	Specification	Test Method
CLASSIFICATION(S):	EN779 - 2002	F7		
BASIS WEIGHT:	(g/m <sup>2</sup> )	120	115-135	EN/ISO 536
THICKNESS:	(mm)	-	-	EN/ISO 534 0.1 N/cm <sup>2</sup>
Air permeability	(l/m <sup>2</sup> s)	465	340-590	EN/ISO 9237
AIRFLOW RESISTANCE:	(Pa)	53	40-66	TSI 8130, 11 cm/sec (21.6 FPM) face velocity)
EFFICIENCY:	(% with 0.3 micron DEHS)	75	68.5-82.5	TSI 8130, 11 cm/sec (21.6 FPM) face velocity)
FLAMMABILITY DATA:	DIN 53438	F1		
	UL			

All product data and statements are indicative of typical properties and characteristics obtainable. This data sheet is to be used as a guide and not as a specification sheet. H&V makes no representation or warranty except as otherwise agreed to in writing between the parties.