



Meltblown Media

100% polypropylene meltblown media, typically designed for pocket and rigid filter applications.

		Target	Specification	Test Method
CLASSIFICATION(S):	EN779 - 2012	F7 EN779:2012		
BASIS WEIGHT:	(g/m ²)	100	80-120	EN/ISO 536
THICKNESS:	(mm)	-	-	EN/ISO 534 0.1 N/cm ²
AIR Permeability:	(l/m ² s)	410	260-560	at 2 mbar EN/ISO 9237 (A=20cm ²)
Resistance	(Pa)	75	≤ 85	TSI 8130, 12.8 cm/sec (25 FPM) face velocity
EFFICIENCY:	(% with 0.3 micron DEHS - discharged IPA)		≥ 35	TSI 8130, 12.8 cm/sec (25 FPM) face velocity
FLAMMABILITY DATA:	DIN 53438	F1		
	UL			