


**Standard HVAC Filter Media**

Low resistance media for HVAC applications Designed to be processed in minipleat applications.

		Target	Specification	Test Method
CLASSIFICATION(S):	EN1822			
BASIS WEIGHT:	(g/m <sup>2</sup> )	68	64-72	BS EN ISO 536
	(lb/3,000ft <sup>2</sup> )	42		
THICKNESS:	(mm)	0.55		2kPa pressure
	(mil)	22		
PENETRATION:	(% with 0.3 micron)	50	55 max	TDA 100P face velocity 5.33 cm/s at 0.3 micron
AIR FLOW RESISTANCE:	(Pa)	30	35 max	5.3 cm/sec (10.5FPM) face velocity
	(inches H <sub>2</sub> O)	0.12		
TENSILE STRENGTH - MD:	(lb/inch)	6.85		Internal
	(kN/m)	1.2	0.7 min	
TENSILE STRENGTH - CD:	(lb/inch)	4.57		Internal
	(kN/m)	0.8	0.5 min	
GURLEY STIFFNESS - MD:	(gu)	800		TAPPI T543
IGNITION LOSS:	(%)	7.5	6.0 -9.0	550° 10 mins
WATER REPELLENCY:	(kPa)	3.0	1.5 min	1 kPa/min
	(inches H <sub>2</sub> O)	12.04		
FLAMMABILITY DATA:	NF P 92-503 (1995)	M1	M1	
	UL			

All product data and statements are indicative of typical properties and characteristics obtainable. This data sheet is to be used as a guide and not as a specification sheet. H&V makes no representation or warranty except as otherwise agreed to in writing between the parties.